

In the Claims:

1. (Original) Method for the manufacture of essentially endless fine threads from meltable polymers, in which polymer melt is spun from at least one spin hole and passed through a Laval nozzle, wherein the spun thread is drawn by gas streams accelerated to high speed by means of the Laval nozzle, and wherein with a given geometry of the melt hole and its position relative to the Laval nozzle the temperature of the polymer melt, its throughput per spin hole and the pressures in front of and behind the Laval nozzle which define the speed of the gas streams are controlled in such a way that the thread before solidification thereof attains a hydrostatic pressure in its interior which is greater than the gas pressure surrounding it, such that the thread bursts and splits into a plurality of fine threads.
2. (Previously Presented) Method according to claim 1, wherein the gas flow around the at least one thread is laminar.
3. (Previously Presented) Method according to claim 1, wherein the space behind the Laval nozzle is at ambient pressure or, in case of further processing of the threads, is at a pressure slightly above ambient pressure, which is necessary for further processing.
4. (Previously Presented) Method according to claim 1, wherein the gas streams which draw the thread are at ambient temperature or a temperature caused by their supply.
5. (Previously Presented) Method according to claim 1, wherein the ratio of the pressures in the space above and below the Laval nozzle when using air is selected between 1.02 and 2.5, depending on the polymer, its throughput and melting temperature.
6. (Previously Presented) Method according to claim 1, wherein the thread emerging from the spin hole is heated by radiation in the region of the Laval nozzle.
7. (Previously Presented) Method according to claim 1, wherein a plurality of threads are spun and split, which are deposited to form a non-woven fabric or further processed into yarns.

8. (Previously Presented) Apparatus with a spinning head connected to a feeder for the melt, a spinning nozzle assembly which is held in the spinning head and comprises at least one spin hole and which spins a melt monofilament, a plate (6') which is located below the spinning head (11) and which comprises a Laval nozzle (6) arranged in a fixed geometrical relationship to the spin hole (4), wherein between plate (6') and spinning head (11) is formed a closed first space (8) provided with a supply of gas (5) and below the plate (6') is provided a second space (7), and wherein the throughput of the melt per spin hole (4), the temperature of the melt and the pressure in the first and second spaces are adjusted in such a way that the spun melt monofilament carried by the flow of gas after leaving the Laval nozzle (6) before solidification thereof attains a hydrostatic pressure which is greater than the gas pressure surrounding it, such that the thread bursts and splits into a plurality of fine threads.

9. (Previously Presented) Apparatus according to claim 8, wherein the spinning assembly (3) is insulated from the first space (8) in the region of the at least one spin hole (4) by an insulating assembly (9) and/or is heated in the region of the at least one spin hole (4).

10. (Previously Presented) Apparatus according to claim 8 wherein the pressure ratios in the first and second spaces (8, 7) are adjusted in such a way that the gas flow in the Laval nozzle (6) attains speeds up to the speed of sound and over.

11. (Previously Presented) Apparatus according to claim 8, wherein the second space (7) is at ambient pressure or a few mbar over.

12. (Previously Presented) Apparatus according to claim 8, wherein the supplied gas is at ambient temperature or the temperature of its feeder.

13. (Previously Presented) Apparatus according to claim 8, wherein the outlet opening of the at least one spin hole (4) in the region of the Laval nozzle (6) is located at the level of the upper edge of the plate (6'), a few mm above the upper edge of the plate, or extends a few mm into the Laval nozzle (6).

14. (Previously Presented) Apparatus according to claim 8, wherein the spinning nozzle assembly comprises a plurality of spin holes (4) which are if occasion arises provided with nipples and which form a row or several parallel rows.
15. (Previously Presented) Apparatus according to claim 8, wherein the plate comprises at least one elongate Laval nozzle.
16. (Previously Presented) Apparatus according to claim 8, wherein the plate comprises a plurality of rotationally symmetrical Laval nozzles.
17. (Previously Presented) Apparatus according to claim 8, wherein a delivery belt is provided for deposition of the threads and formation of a non-woven fabric.
18. (Previously Presented) Apparatus according to claim 8, wherein a winding device is provided for winding the threads.
19. (Previously Presented) Non-woven fabric made from threads manufactured from meltable polymers, in which polymer melt is spun from at least one spin hole and passed through a Laval nozzle, wherein the spun thread is drawn by gas streams accelerated to high speed by means of the Laval nozzle, and wherein with a given geometry of the melt hole and its position relative to the Laval nozzle the temperature of the polymer melt, its throughput per spin hole and the pressures in front of and behind the Laval nozzle which define the speed of the gas streams are controlled in such a way that the thread before solidification thereof attains a hydrostatic pressure in its interior which is greater than the gas pressure surrounding it, such that the thread bursts and splits into a plurality of fine threads.
20. (Previously Presented) Yarns made from threads which have been produced from meltable polymers, in which polymer melt is spun from at least one spin hole and passed through a Laval nozzle, wherein the spun thread is drawn by gas streams accelerated to high speed by means of the Laval nozzle, and wherein with a given geometry of the melt hole and its position relative to the Laval nozzle the temperature of the polymer melt, its throughput per spin hole and the pressures in front of and behind the Laval nozzle which

define the speed of the gas streams are controlled in such a way that the thread before solidification thereof attains a hydrostatic pressure in its interior which is greater than the gas pressure surrounding it, such that the thread bursts and splits into a plurality of fine threads.


Applicants do not believe that any fees are due at this time; however, should any fees under 37 C.F.R. §§ 1.16 to 1.21 be required for any reason relating to this document, the Commissioner is authorized to deduct the fees from Deposit Account No. 02-0383, (*formerly Baker & Botts, L.L.P.*) Order Number (073306.0101).

If the Examiner feels that a telephone conference or an interview would advance prosecution of this Application in any manner, the undersigned agent for Applicant stands ready to conduct such a conference at the convenience of the Examiner.

Respectfully submitted,

Date: October 14, 2003

By: _____



Andreas H. Grubert
(Limited recognition 37 C.F.R. §10.9)
One Shell Plaza
910 Louisiana Street
Houston, Texas 77002-4995
Telephone: 713.229.1964
Facsimile: 713.229.7764
AGENT FOR APPLICANTS